NC/QC/YD/2019-20/W3-DL-C1

Date: 23-11-2019

1. TEST REPORT ON CEMENT:

Sub: Testing of 53 Grade Cement Sample (IS 12269-1987).
{Project*: Improvements to roads and drains at Doddabettahalli layout in Ward No. 03.}
Ref.: Material testing/PMC/19-20,
Report Required for: Assistant Executive Engineer,
Yelahanka Satellite Town Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

PHYSICAL TESTS ON CEMENT

Grade * : 53,
Type * : O.P.C

TABLE 1.1:

SL No	Name of Test	Test Results	Requirements as per IS 8112-1989
1	Initial setting time	**158 min**	Shall not be less than 30 min
2	Final setting time	**285min**	Shall not be more than 600 min
3	Fineness (by dry sieving on IS 90 micron sieve)	**2.13%**	Not to exceed 10.0%
4	Soundness test(by Le-Chatelier's method)	**2.09 mm**	Shall not be more than 10 mm
5	Compressive strength a) 3 days (average of three results)	**28.75 N/Sq mm**	Shall not be less than 27 N/Sqmm

NEWZEN CONSULTANTS * BANGALORE *

K.R
KIRAN. R
M.E, (Civil-Engg)

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 9703630301

NC/QC/YD/2019-20/W3-DL-PCC1

Date: 23-11-2019

1. TESTING OF COARSE AND FINE AGGREGATES:

Sub: Testing of Coarse and Fine aggregates to be used for bed concrete.
{Project*: Improvements to roads and drains at Doddabettahalli layout in Ward No. 03.}
Ref.: Material testing/PMC/19-20,
Report Required for: Assistant Executive Engineer,
Yelahanka Satellite Town Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

1. COARSE AGGRGATES TABLE - SIEVE ANALYSIS:

IS Sieve Size, mm	Percentage passing	Requirements as per IS 383-1970 (Reaffirmed on 2007) % Passing	
	40 mm Sample	Single size	Graded
40mm	100.00	85-100	90 – 100
20mm	68.20	0 -20	30- 70
10mm	27.30	0 -5	10- 35
4.75mm	4.15	------	0- 5

2. FINE AGGREGATES TABLE - SIEVE ANALYSIS:

IS Sieve Size, mm	Percentage Passing	Specification as Per IS: 383-1970(Reaffirmed 2002) Percentage Passing			Remarks
		Zone-I	Zone-II	Zone -III	
04.75	96.30	90-100	90-100	90-100	The Sample Conforms to Grading **Zone-II**
02.36	84.25	60-95	75-100	85-100	
01.18	76.80	30-70	55-90	75-100	
600.mic	54.35	15-34	35-59	60-79	
300.mic	16.90	5-20	8-30	12-40	
150.mic	8.15	0-10	0-10	0-10	

NEWZEN CONSULTANTS BANGALORE

KIRAN. R
M.E, (Civil-Engg)

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187

NC/QC/YD/2019-20/W3-DL-CB1

Date: 09-12-2019

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements to roads and drains at Doddabettahalli layout in Ward No. 03.}
Ref.: Material testing/PMC/19-20,
Report Required for: Assistant Executive Engineer,
Yelahanka Satellite Town Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	02-12-19	09-12-19	07	22500	365	16.22	16.30
	002	"	"	"	"	360	16.00	
	003	"	"	"	"	375	16.67	

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರ
ಯಲಹಂಕ ಉಪನಗರ ಉಪವಿಭಾಗ,
ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬೆಂಗಳೂರು-64

NEWZEN CONSULTANT * BANGALORE

KIRAN. R
M.E, (Civil-Engg)

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187

Date: 10-12-2019

NC/QC/YD/2019-20/W3-DL-CB2

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements to roads and drains at Doddabettahalli layout in Ward No. 03.}
Ref.: Material testing/PMC/19-20,
Report Required for: Assistant Executive Engineer,
Yelahanka Satellite Town Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	03-12-19	10-12-19	07	22500	370	16.44	16.22
	002	"	"	"	"	365	16.22	
	003	"	"	"	"	360	16.00	

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರ ಯಲಹಂಕ ಉಪನಗರ ಉಪವಿಭಾಗ ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬೆಂಗಳೂರು-106

NEWZEN CONSULTANT * BANGALORE *

KIRAN. R
M.E, (Civil-Engg)

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

NC/QC/YD/2019-20/W3-DL-CB5

Date: 30-12-2019

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements to roads and drains at Doddabettahalli layout in Ward No. 03.}
Ref.: Material testing/PMC/19-20,
Report Required for: Assistant Executive Engineer,
Yelahanka Satellite Town Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*. M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	23-12-19	30-12-19	07	22500	375	16.67	16.74
	002	"	"	"	"	385	17.11	
	003	"	"	"	"	370	16.44	

NEWZEN CONSULTANT * BANGALORE *

KIRAN. R
M.E, (Civil-Engg)

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187

Date: 30-12-2019

NC/QC/YD/2019-20/W3-DL-CB1A

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to roads and drains at Doddabettahalli layout in Ward No. 03.}
Ref.: Material testing/PMC/19-20,
Report Required for: Assistant Executive Engineer,
Yelahanka Satellite Town Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	02-12-19	30-12-19	29	22500	495	22.00	22.22
	002	"	"	"	"	500	22.22	
	003	"	"	"	"	505	22.44	

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಯಲಹಂಕ ಉಪನಗರ ಉಪವಿಭಾಗ,
ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬೆಂಗಳೂರು-106

NEWZEN CONSULTANT * BANGALORE *

KIRAN. R
M.E, (Civil-Engg)

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

NC/QC/YD/2019-20/W3-DL-CB4A

Date: 10-01-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to roads and drains at Doddabettahalli layout in Ward No. 03.}
Ref.: Material testing/PMC/19-20,
Report Required for: Assistant Executive Engineer,
Yelahanka Satellite Town Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	13-12-19	10-01-20	28	22500	525	23.33	22.96
	002	"	"	"	"	515	22.89	
	003	"	"	"	"	510	22.67	

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಯಲಹಂಕ ಉಪನಗರ ಉಪವಿಭಾಗ
ಬ ಮ ಪ.ಪ. ಬೆಂಗಳೂರು-106

NEWZEN CONSULTANT * BANGALORE

KIRAN. R
M.E, (Civil-Engg)

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187

NC/QC/YD/2019-20/W3-DL-CB6A

Date: 21-01-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to roads and drains at Doddabettahalli layout in Ward No. 03.}
Ref.: Material testing/PMC/19-20,
Report Required for: Assistant Executive Engineer,
Yelahanka Satellite Town Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	24-12-19	21-01-20	28	22500	525	23.33	22.96
	002	"	"	"	"	515	22.89	
	003	"	"	"	"	510	22.67	

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಯಲಹಂಕ ಉಪನಗರ ಉಪವಿಭಾಗ
ಬ.ಬೃ.ಮ. ಬೆಂಗಳೂರು-106

NEWZEN CONSULTANT * BANGALORE

KIRAN. R
M.E, (Civil-Engg)

NC/QC/YD/2019-20/W3-DL-K2

Date: 25-01-2020

TEST REPORT

Sub: Testing of Pre-cast Material-Kerb Stones.
{Project*: Improvements to roads and drains at Doddabettahalli layout in Ward No. 03.}
Ref.: Material testing/PMC/19-20,
Report Required for: Assistant Executive Engineer,
Yelahanka Satellite Town Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore

1. PHYSICAL TESTS ON KERB STONES :

Sl No.	Identification	Flexural strength, fcr in N/sqmm	Characteristic Compressive Strength, fck in N/sqmm	Avg. Characteristic. Compressive Strength fck in N/sqmm	Remarks
1	001	3.31	22.40	22.98	As per Cl. 6.2.2 of IS 456-2000, fcr=0.7√ fck
2	002	3.39	23.45		
3	003	3.36	23.10		

2. WATER ABSORPTION TEST

Sl No	Identification	Water absorption %	Average value %
1	001	4.59	4.64
2	002	4.71	
3	003	4.64	

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಯಲಹಂಕ ಉಪನಗರ ಉಪವಿಭಾಗ,
ಪ.ಪಂ.ಕ. ಬೆಂಗಳೂರು-106

NEWZEN CONSULTANT * BANGALORE *

Page No. 1/1

KIRAN.
M.E, (Civil-Eng

NC/QC/YD/2019-20/W3-DL-K3

Date: 29-01-2020

TEST REPORT

Sub: Testing of Pre-cast Material-Kerb Stones.
{Project*: Improvements to roads and drains at Doddabettahalli layout in Ward No. 03.}
Ref.: Material testing/PMC/19-20,
Report Required for: Assistant Executive Engineer,
Yelahanka Satellite Town Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

1. PHYSICAL TESTS ON KERB STONES :

Sl No.	Identification	Flexural strength, fcr in N/sqmm	Characteristic Compressive Strength, fck in N/sqmm	Avg. Characteristic. Compressive Strength fck in N/sqmm	Remarks
1	001	3.37	23.20	22.15	As per Cl. 6.2.2 of IS 456-2000, fcr=0.7√ fck
2	002	3.24	21.45		
3	003	3.27	21.80		

2. WATER ABSORPTION TEST

Sl No	Identification	Water absorption %	Average value %
1	001	5.05	5.82
2	002	4.74	
3	003	4.69	

NEWZEN CONSULTANT * BANGALORE *

KIRAN. P
M.E, (Civil-E

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com